




Maintenance-Free Rechargeable Sealed Lead-Acid Battery




BP8-6H

The battery is constructed by plates, separators, safety valves and container. Since the electrolyte is held by a glass-mat separator and plates, the battery can use in any direction and position without leakage.

PERFORMANCE SPECIFICATIONS


Nominal Voltage(V)	6 volts(3cells in series)
Nominal Capacity(AH)	
20 Hour rate F.V.(1.75V/cell) (400A to 5.25volts)	8.0A.H.
10 Hour rate F.V.(1.75V/cell) (760A to 5.25volts)	7.6A.H.
5 Hour rate F.V.(1.75V/cell) (1360A to 5.25volts)	6.8A.H.
1 Hour rate F.V.(1.55V/cell) (4800A to 4.65volts).....	4.8A.H.
Approximate Weight	1350g(2.98lbs.)
Terminal	
Standard.....	Type T1
Optional.....	Type T2
Internal Resistance (Fully Charged Battery)	<12.5m Ω
Maximum Discharge Current For 5 sec.(A)	120A
Maximum Charge Current(A)	2.40A
Ambient Temperature	
Charge.....	0°C(32°F)~40°C(104°F)
Discharge.....	-20°C(-4°F)~50°C(122°F)
Storage.....	-20°C(-4°F)~40°C(104°F)
Vibration test:	
Frequency: 16.7HZ	
Amplitude: 4mm	
Vibrate the battery horizontally or vertically for 60 minutes.The battery have no abnormality.	
Case	ABS
Dimension(mm/inch)	
Length ±1.5mm.....	151/5.94
Width ±1.5mm.....	34/1.34
Container Height ±1.5mm.....	94/3.70
Total Height ±2mm.....	100/3.94
Application	Electronic Toy-Cars.Emergency Lights,Rechargeable Flashlights,UPS,Fans

BP8-6H Battery discharge characteristics (25°C/77°F)



BATTERY CHARGING CHARACTERISTICS

(Typical example of the charge characteristic for the standby use)




Charging Procedure

Application	Charging method	Charging Voltage at 20°C (V/cell)	Temperature compensation coefficient of charging voltage (mV/°C/cell)	Max. charging current (CA)	Charging time 0.1CA, 20°C (h)		Temp (°C)
					100% discharge	50% discharge	
For standby power Source	Constant voltage & Constant current charging (with current restriction)	2.25~2.30	-3	0.3	24	20	0~40 (32~104°F)
For cycle service		2.40~2.50	-4	0.3	16	10	


*Temperature compensation of charging voltage is not needed, when using the batteries within 5°C to 35°C range.

Effect of Temperature on Long Term Float Life




TERMINAL TYPE

mm(inch)



OUTER DIMENSIONS


mm(inch)



Constant power discharge characteristics at 25°C/77°F

Final Voltage	Discharge time									
	5Min	10Min	15Min	30Min	1Hr	3Hr	5Hr	10Hr	20Hr	
5.40V	144.6	106.5	85.3	50.8	29.11	11.66	8.04	4.49	2.35	
5.25V	167.4	115.3	89.2	52.7	29.99	11.89	8.16	4.56	2.40	
5.10V	177.9	119.5	92.0	53.9	30.52	12.00	8.20	4.58	2.41	
4.95V	185.8	122.4	94.1	54.7	30.89	12.08	8.23	4.60	2.42	
4.80V	192.0	124.8	96.0	55.2	31.20	12.16	8.26	4.60	2.42	

TERMINAL POSITION



B.B. BATTERY CO., LTD. Web Site: <http://www.bb-battery.com>

USA :

B&B BATTERY (USA) INC.
6415 RANDOLPH ST. COMMERCE,
CA, 90040 U.S.A.
TEL: 1-323-278-1900 . 1-800-278-8599
FAX: 1-323-278-1268

CHINA FACTORY:

CHENG DONG TRIAL AREA, HUANG GANG,
RAOPING GUANG DONG, CHINA, 515700
TEL: 86-768-7601001-2
FAX: 86-768-7601469

UK:

B & B BATTERY (UK) CO., LTD.
TEL: 44-161-343-7430
FAX: 44-161-343-7030

HONG KONG OFFICE:

NATIONAL TRADING LTD.
TEL: 852-2301-3800
FAX: 852-2739-1182

JAPAN:

B & B BATTERY (JAPAN) CO., LTD.
TEL: 81-426-256-537
FAX: 81-426-256-537

TAIWAN OFFICE:

B & B BATTERY CO., LTD.
TEL: 886-6-2607335
FAX: 886-6-2602402



MH19884

