



惠州基安比新能源有限公司
Huizhou Markyn New Energy Co., LTD.

锂电池UN38.3测试报告

Lithium Battery UN38.3 Test Report

Sample Description

& Model Polymer Li-ion Cell GMBT353533

Applicant Huizhou Markyn New Energy Co., L !.

Manufacturer Huizhou Markyn New Energy Co., L !.



1. SAMPLES DESCRIPTION

Sample Name	Polymer Li-ion Cell	Sample Model	GMBT353533		
Manufacturer	Huizhou Markyn New Energy Co., Ltd.				
Nominal Voltage	3.5V	Sample Capacity	35-mAh	Limit Charge Voltage	7.03V
Charge Current	35-mA	Maximum Continuous Current	35-mA	End Charge Current	35-mA
Cutoff Voltage	3.0V	Maximum Discharge Current	35-mA	Self-discharge Rate	Typical
Cell Number	1PC+	Cell Model	GMBT353533	Cell Capacity	35-mAh
Manufacturer Code	GMB				
Chemical Composition	LiCo&O				
Classification	0-12.10.1	Classification	0-12.10.5		

II REFERENCE METHOD

"ni e! Na ion# \$e#ommen!a ion# &n The Tran# 'or &() angerou# Goo!#,Manual &(Te# # *n! Cri eria.
(+T,+G,*C.1-,11,\$e..5,*men!.1 / +T,+G,*C.1-,11,\$e..5,*men!.0)

III TEST ITEM

- 1. *I i u!e #imula ion 5.E1 ernal #hor %ir%ui
- 0. Thermal e# 2. Cru#h
- 3. 3i4ra ion 5. 6or%e! !i#%harge
- 7. +ho%k

IV CONCLUSION

ITEM	Sample Name	Sample No.	C&NCL "+&&N
I i u!e #imula ion	N19N1-	" N3:.3	P++
Thermal e#			P*++
3i4ra ion			P*++
+ho%k			P*++
E1 ernal #hor %ir%ui			P*++
Cru#h			P*++
6or%e! !i#%harge	N119N15 N0-9N0; C59C17		P*++

The #u4mi e! %ell an! %om'onen %ell %om'lie! wi h he "N Manual o(Te# # an! Cri eria,'ar 888,#u4-#e% ion 3: .3.

Pre'are! 4y < Che%ke! 4y

8##ue)a e< 0-12-10-5





Notes:

N1~N10,N16~N19:Cells at first cycle in fully charged states;

N11~N15:Cells at first cycle at 50% of the design rated capacity;

N20~N29:Cells after 50 cycles in fully discharged states;

C1~C4:Cells after 50 cycles ending in fully charged states;

C5~C14:Cells after 50 cycles ending in fully discharged states;

V、PHOTO OF THE SAMPLE



Authenticate the photo on original report only



惠州基安比新能源有限公司
Huizhou Markyn New Energy Co., LTD.



T.3 Vibration

Cells and batteries are firmly secured to the platform of the vibration machine without distorting the cells in such a manner as to faithfully transmit the vibration. The vibration shall be a sinusoidal waveform with a logarithmic sweep between 7Hz and 200Hz and back to 7Hz traversed in 15 minutes. This cycle shall be repeated 12 times a total of 3 hours for each of three mutually perpendicular mounting positions of the cell .One of the directions of vibration must be perpendicular to the terminal face

The logarithmic frequency sweep shall differ for cells and batteries with a gross mass of not more than 12 kg(cells and small batteries),and for batteries with a gross mass of more than 12 kg(large batteries).

For cells and small batteries from 7Hz a peak acceleration of 1gn is maintained until 18Hz is reached. The amplitude is then maintained at 0.8mm(1.6mm total excursion) and the frequency increased until a peak acceleration of 8 gn occurs (approximately 50 Hz) .

A peak acceleration of 8 gn is then maintained until the frequency is increased to 200Hz.

For large batteries from 7Hz to a peak acceleration of 1 gn is maintained until 18Hz is reached. The amplitude is then maintained at 0.8mm (1.6mm total excursion) and the frequency increased until a peak acceleration of 2 gn occurs (approximately 25Hz) .A peak acceleration of 2 gn is then maintained until the frequency is increased to 200Hz.

Cells and batteries meet this requirement if there is no leakage, no disassembly, no rupture and fire during the test and if the open circuit voltage of each test cell or battery directly after testing in its third perpendicular mounting position is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not application to test cells and batteries at fully discharged states.

T.4 Shock

Test cells and batteries shall be secured to the testing machine by means of a rigid mount which will support all mounting surfaces of each test battery. Each cell or battery shall be subjected to a half-sine shock of peak acceleration of 150 gn and pulse duration of 6 milliseconds. Each cell or battery shall be subjected to three shocks in the direction followed by three shocks in the negative direction of three mutually perpendicular mounting positions of the cell or battery for a total of 18 shocks.

However ,large cells and large batteries shall be subjected to a half- sine shock of peak acceleration of 50 gn and pulse duration of 11 milliseconds. Each cell or battery is subjected to three shocks in the positive direction followed by three shocks in the negative direction of each of three mutually perpendicular mounting position of the cell for a total of 18 shocks.

Cells and batteries meet this requirement if there no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test or battery after testing is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test and batteries at fully discharged states.



惠州基安比新能源有限公司
Huizhou Markyn New Energy Co., LTD.



惠州基安比新能源有限公司
Huizhou Markyn New Energy Co., LTD.



惠州基安比新能源有限公司
Huizhou Markyn New Energy Co., LTD.



3. Vibration

NO.	Pre-test		After test		Mass loss(%)	Voltage loss (%)	Whether leakage, Venting, disassembly, Rupture, fire(Y/N)
	Mass (g)	Voltage (V)	Mass (g)	Voltage (V)			
N1	8.021	3.71	8.021	3.71	0.000	0.00	N
N2	8.101	3.69	8.101	3.70	0.000	0.27	N
N3	8.006	3.70	8.006	3.70	0.000	0.000	N
N4	8.025	3.71	8.025	3.70	0.000	0.027	N
N5	8.003	3.70	8.003	3.69	0.020	0.027	N
N6	8.113	3.69	8.113	3.68	0.000	0.27	N
N7	8.012	3.69	8.012	3.69	0.000	0.000	N
N8	8.031	3.71	8.031	3.71	0.000	0.000	N
N9	8.007	3.70	8.007	3.70	0.000	0.000	N
N10	8.023	3.70	8.023	3.70	0.000	0.000	N

4. Shock

NO.	Pre-test		After test		Mass loss(%)	Voltage loss (%)	Whether leakage, Venting, disassembly, Rupture, fire(Y/N)
	Mass (g)	Voltage (V)	Mass (g)	Voltage (V)			
N1	8.021	3.71	8.021	3.71	0.000	0.00	N
N2	8.101	3.69	8.101	3.70	0.000	0.27	N
N3	8.006	3.70	8.006	3.70	0.000	0.000	N
N4	8.025	3.71	8.025	3.70	0.000	0.027	N
N5	8.003	3.70	8.003	3.69	0.020	0.027	N
N6	8.113	3.69	8.113	3.68	0.000	0.27	N
N7	8.012	3.69	8.012	3.69	0.000	0.000	N
N8	8.031	3.71	8.031	3.71	0.000	0.000	N
N9	8.007	3.70	8.007	3.70	0.000	0.000	N
N10	8.023	3.70	8.023	3.70	0.000	0.000	N



惠州基安比新能源有限公司
Huizhou Markyn New Energy Co., LTD.



7. Forced discharge

NO.	Whether disassembly, fire (Y/N)
N20	N
N21	N
N22	N
N23	N
N24	N
N25	N
N26	N
N27	N
N28	N
N29	N
C5	N
C6	N
C7	N
C8	N
C9	N
C10	N
C11	N
C12	N
C13	N
C14	N

*****End of report*****